

Abstract

A method of manufacturing a semiconductor device comprising forming an insulating layer above a semiconductor layer, forming a conductive layer including at least tantalum and tantalum nitride, and etching the conductive layer with using a gas including SiCl_4 and NF_3 .